

PRO Collection | Solid 3/4" x 3 1/4" platform



Product Technical Specifications

Nature of material	100% Hardwood
Dimensions	Thickness: 3/4" (19 mm) Width: 3 1/4" (83 mm) Lengths: Random, from 12" to 84" (305 mm to 2 134 mm) May occasionally include a few planks of an inferior length
Profiling	Micro v-joint on 4 sides
Moisture content	Between 6% and 9%
Species and Janka hardness (lb)	Red Oak (1 290), Hard Maple (1 450)
Available grade	PRO
Colors	Refer to the PRO Collection section of the current Mercier Product Chart
Accessories	T-Moldings, Quarter Rounds, Thresholds, Reducers and Stair nosings, according to the wood species Touch-up kits, Maintenance kit
Manufacturing	Manufactured, stained and finished in Canada by Mercier Wood Flooring

Finish and Warranties



liv Finish

Acrylate polymer-based finish consisting of plant-based oil and UV-cured polymer and reinforced with suspended aluminum oxide particles.

Available glosses: PRO (30°) and PRO-brushed (10°), according to the wood species.

Warranties

20 years for normal residential use
Structural lifetime warranty

Non-yellowing: The non-yellowing formula in the finishes reduces the natural wood board yellowing process.

Antimicrobial: The antimicrobial contained in our finishes helps reduce the risk of spreading bacteria and mildew. Completely non-toxic, this special treatment adds an additional level of protection for healthier floors.

Packaging	Number of boxes	Content	Width	Length	Height	Weight
Box		22 sq. ft. (2 m ²)	10"	87"	3 1/4"	60 lb (27 kg)
Pallet	40	880 sq. ft. (81.8 m ²)	42"	87"	36"	2 200 to 3 000 lb (998 to 1 361 kg)

PRO Collection | Solid 3/4" x 3 1/4" platform

Installation

Types of installation	Nailed or Stapled
Relative humidity	Between 35% and 55%
Subfloor	<ul style="list-style-type: none"> • OSB or 3/4" (19 mm) plywood Joists spaced no more than 19" (48 cm) C-C • 5/8" (16 mm) plywood Joists spaced no more than 16" (41 cm) C-C
Installation sites	First floor and upper floors
Radiant heated floor	No

VOC / Formaldehyde

VOC-free and formaldehyde-free finish: ASTM D-5116

Greenguard Gold certification: Applies to all species, widths and colors.

Phtalate-free finish: OSHA method 104

Maximum Greenguard Gold emission criteria

TVOC	≤ 0.22 mg/m ³
Formaldehyde	≤ 0.0073 ppm
Total Aldehydes	≤ 0.043 ppm
IVOCs	≤ 1/100 TLV and 1/2 chronic REL

Applicable standards

Surface burning ASTM-E-84	Class C (varies according to the wood species) Flame Spread Index: 100 to 150 Smoke Development: 75 to 400 according to the wood species
Surface burning CAN/ ULC-S102.2	Flame Spread Index (FSR): 130 Smoke Development (SDC): 255
Abrasion resistant finish (Taber test)	liv finish: ASTM D4060: 1 000 cycles
Static friction coefficient ASTM D2394	liv finish PRO: 0.57 PRO-brushed: 0.68

Certifications



CONTRIBUTION
TO THE CERTIFICATION
LEED®

The information in this document was accurate at the time of publication. Mercier Wood Flooring reserves the right to change the products or products characteristics at any time without notice.