

Engineered 3/4" x 5" platform



Product Technical Specifications

Nature of material	Top layer: Hardwood, 4 mm thick Base: Plywood
Dimensions	Thickness: 3/4" (19 mm) Width: 5" (127 mm) Lengths: Random, from 12" to 83" (305 mm to 2 108 mm) May occasionally include a few planks of an inferior length
Profiling	Micro v-joint on 4 sides
Moisture content	Between 6% and 9%
Species and Janka hardness (lb)	White Oak (1 360), Red Oak (1 290), Hard Maple (1 450), Hickory (1 820), White Ash (1 320)
Available grades	Select & Better, Distinction and Authentic
Colors	Refer to the current Mercier Product Chart
Accessories	T-Moldings, Quarter Rounds, Thresholds, Reducers and Stair nosings, according to the wood species Touch-up kits, Maintenance kit
Manufacturing	Manufactured, stained and finished in Canada by Mercier Wood Flooring

Finishes and Warranties



liv Finish

Acrylate polymer-based finish consisting of plant-based oil and UV-cured polymer and reinforced with suspended aluminum oxide particles.

Available glosses: Satin (30°), Matte and Matte-brushed (10°), according to the wood species.

Warranties

35 years for normal residential use
5 years for light commercial use
Structural lifetime warranty



livUP Finish

Finish composed of plant-based oil and microfragmented aluminum particles (Al_2O_3) in suspension in a UV-cured polyurethane resin.

Available gloss: Matte (10°)

Warranties

50 years for normal residential use
10 years for light commercial use
3 years for commercial use with direct outdoor access
Structural lifetime warranty

Non-yellowing: The non-yellowing formula in the finishes reduces the natural wood board yellowing process.

Antimicrobial: The antimicrobial contained in our finishes helps reduce the risk of spreading bacteria and mildew. Completely non-toxic, this special treatment adds an additional level of protection for healthier floors.

Packaging	Number of boxes	Content	Width	Length	Height	Weight
Box		22 sq. ft. (2 m ²)	10"	87"	3 1/4"	63 lb (28 kg)
Pallet	40	880 sq. ft. (81.8 m ²)	42"	87"	36"	2 700 to 3 000 lb (1 225 to 1 361 kg)

Engineered 3/4" x 5" platform

Installation

Types of installation	Nailed, Glued, Stapled or Floating
Relative humidity	Between 30% and 65%
Subfloor	<ul style="list-style-type: none"> • OSB or 3/4" (19 mm) plywood Joists spaced no more than 19" (48 cm) C-C • 5/8" (16 mm) plywood Joists spaced no more than 16" (41 cm) C-C • Concrete slab
Installation sites	Basement, first floor and upper floors
Radiant heated floor	Yes. Refer to the Technical bulletin #5 for more details.* (*Except Hickory)

VOC / Formaldehyde

VOC-free and formaldehyde-free finish: ASTM D-5116

Greenguard Gold certification: Applies to all species, widths and colors.

Phtalate-free finish: OSHA method 104

TSCA Title VI compliant & CANFER compliant

Maximum Greenguard Gold emission criteria

TVOC	≤ 0.22 mg/m ³
Formaldehyde	≤ 0.0073 ppm
Total Aldehydes	≤ 0.043 ppm
IVOCs	≤ 1/100 TLV and 1/2 chronic REL

Applicable standards

Surface burning ASTM-E-84	Class C (varies according to the wood species) Flame Spread Index: 100 to 150 Smoke Development: 75 to 400 according to the wood species
Surface burning CAN/ ULC-S102.2	Flame Spread Index (FSR): 130 Smoke Development (SDC): 255
Abrasion resistant finish (Taber test)	liv finish: ASTM D4060: 1 000 cycles livUP finish: ASTM D4060: 2 500 cycles
Static friction coefficient ASTM D2394	liv finish (according to the gloss) Satin: 0.57 Matte and Matte-brushed: 0.68 livUP finish Matte: 0.56

Certifications



CONTRIBUTION
TO THE CERTIFICATION
LEED®

The information in this document was accurate at the time of publication. Mercier Wood Flooring reserves the right to change the products or products characteristics at any time without notice.